DATA

FP12-24FR



www.fulbat.com - @ FULBAT








FP Series are general purpose batteries with 5 years design life in float service. With advanced AGM valve regulated technology and high purity raw material, the FP series batteries ensure high performance and reliable standby service life. They have been designed specifically for applications such as security & alarm systems, UPS, Telecom, power grid, medical equipment and emergency lighting. It can also be used for light cycling use. For intensive cycling, the FPC or FPG cyclic ranges are recommended.


DIMENSIONS & WEIGHT

LENGHT	166±2mm
WIDTH	175±2mm
TOTAL HEIGHT	125±2mm
	T = 5: ()
l WFIGHT	1 77kn (tolerance + 3%)



<u> </u>	

TERMINAL (MM)



SPECIFICATION								
Nominal voltage	12V (6 cells)							
Nominal capacity	24Ah (20hr)							
Design life	5 years at 20°C							
Internal resistance	Approx 14mΩ							
Terminal	Т3							
Max. discharge current	360A (5 sec)							
Reference capacity	24.0Ah (20hr, 1.80V/cell, 25°C/77°F) 22.3Ah (10hr, 1.80V/cell, 25°C/77°F) 20.4Ah (5hr, 1.75V/cell, 25°C/77°F) 18.4Ah (3hr, 1.75V/cell, 25°C/77°F) 15.1Ah (1hr, 1.60V/cell, 25°C/77°F)							
Charge voltage Standby use voltage	13.5V ~ 13.8V 25°C/77°F Temperature compensation: -10mV/°C/Cell							
Cycle use voltage	14.4V ~ 15.0V 25°C/77°F Temperature compensation: -15mV/°C/Cell							
Operating temp. range	Discharge: -15°C ~ 50°C Charge: 0°C ~ 40°C Storage: -15°C ~ 40°C							
Nominal operating temp. range	25°C ± 3°C / 77°F ± 5°F							
Self discharge	Can be stored for up to 6 months at 25°C/77° and then recharging is recommended. Month self-discharge ratio is less than 3% at 25°C/77°							
Capacity affected by temp.	40°C/104°F 103% 25°C/77°F 100% 0°C/32°F 86%							
Container material	Flame Retardant UL94-VO							

APPLICATIONS









Data Center

Emergency Lighting

APPROVALS

ISO9001 - Quality management system ISO14001 - Environnmental management System Approved for transport by Air (IATA) Designed in accordance with IEC 60896-21/22



DATA SHEET

FP12-24FR



www.fulbat.com - @ FULBAT


CONSTANT CURRENT DISCHARGE (AMPERES) AT 25°C/77°F

F.V/Time	5min	10min	15min	20min	30min	45min	1h	2 h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	45.7	35.1	29.1	25.1	19.4	14.32	12.07	7.14	5.58	4.54	3.70	3.21	2.59	2.16	1.19
1.80V/cell	61.3	44.8	35.1	29.7	22.9	16.7	13.52	7.79	6.01	4.85	3.97	3.45	2.75	2.23	1.20
1.75V/cell	69.2	49.3	38.4	32.0	23.8	17.3	14.14	8.08	6.12	4.96	4.08	3.54	2.80	2.29	1.21
1.70V/cell	76.2	53.7	41.0	33.6	24.8	18.0	14.59	8.28	6.29	5.09	4.18	3.61	2.84	2.34	1.23
1.65V/cell	84.0	58.0	43.6	35.7	26.1	18.4	14.93	8.40	6.56	5.26	4.30	3.69	2.88	2.39	1.25
1.60V/cell	92.6	62.9	46.6	38.0	27.6	19.2	15.07	8.76	6.76	5.43	4.44	3.77	2.91	2.41	1.26


CONSTANT POWER DISCHARGE (WATTS/CELL) AT 25°C/77°F

F.V/Time	5min	10min	15min	20min	30min	45min	1h	2 h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	83.6	64.8	54.3	47.4	37.0	27.5	23.3	13.9	10.9	8.88	7.26	6.32	5.12	4.28	2.35
1.80V/cell	111.0	81.9	64.7	55.2	43.0	31.8	25.9	15.0	11.6	9.43	7.76	6.75	5.41	4.41	2.37
1.75V/cell	122.5	88.5	69.8	58.8	44.3	32.6	27.0	15.5	11.8	9.60	7.93	6.91	5.49	4.52	2.39
1.70V/cell	131.1	94.3	73.4	61.3	45.9	33.8	27.8	15.9	12.1	9.84	8.12	7.04	5.56	4.61	2.44
1.65V/cell	142.5	100.8	77.5	64.7	48.0	34.4	28.2	16.0	12.6	10.1	8.32	7.18	5.64	4.70	2.47
1.60V/cell	153.6	107.0	81.5	81.5	50.3	35.6	28.3	16.6	12.9	10.4	8.56	7.31	5.68	4.74	2.48


DISCHARGE CHARACTERISTICS



TEMPERATURE EFFECTS IN RELATION TO BATTERY CAPACITY




CYCLE LIFE IN RELATION TO DEPTH OF DISCHARGE




Testing condition Discharging:current 0.17C A(FV1.7V/cell); Charging:current 0.25C max, voltage 2.45V/cell; Charging volume:125% of discharged cancelty. capacity.


FLOAT CHARGING CHARACTERISTICS



EFFECT OF TEMPERATURE ON LONG TERM FLOAT LIFE



SELF DISCHARGE CHARACTERISTICS



Storage Times (Months)

- No supplementary charge required (carry out supplementary charge before use if 100% capacity is required)
- Supplementary charge required before use. Optional
 - charging way as below:

 1. Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell
- Charged for above 20 hours at limted current 0.25CA and constant voltage 2.45V/cell
 Charged for 8-10 hours at limited current 0.05CA
- Supplementary charge may often fail to recover the capacity. The battery should never be left standing till this is reached

